

5/3: WestCHEM Flooring & Coating Systems

**SOLVA
STRONG**[®]
RANGE OF
CONSTRUCTION CHEMICALS



EPOXY FLOORING TC (TOPCOAT)

About Product

This is two-part Low viscosity, solvent-free epoxy resin system For use in industrial and commercial areas, epoxy floor coating with a smooth, self-leveling surface.

Uses:

It is used to enhance the lifespan and finish of the floor surface. It is suitable for:

- 1: Concrete & plastered surfaces in factories.
- 2: Warehouses.
- 3: Chemical Plants.
- 4: Workshops.
- 5: Car-parks
- 6: Clean rooms.
- 7: Food processing areas
- 8: Service areas
- 9: Kitchens & domestic houses.

Advantages:

- 1: Environmentally friendly.
- 2: Low viscosity.
- 3: Simple to Apply.
- 4: Longer pot life.
- 5: Useful for self-levelling floors.
- 6: Aesthetically pleasing-enhances the working environment.
- 7: Seamless finish.
- 8: Easy to clean & maintain.
- 9: High abrasion resistant.
- 10: Can be used for decorative coating.

Product Information:

Color:	2 Max
Solids:	98 Min
Viscosity:	50~150
Density:	0.99-1.05
Flash Point:	>60
Gel Time:	20~25
Compressive Strength:	>70 mPas
Curing Details:	Full Cure: 7 days.

Application Method

This product should be applied after a primer and a base coat have been applied.

Use **DO NOT MIX BY HAND, USE A STIRRER**. Before blending the ingredients in the specified ratio, fully combine them. First, combine the resin and pigment, then add the filler and thoroughly mix. Finally, before transferring it to a pot, combine it with a hardener and utilise it. Pouring the liquid over the surface and spreading it with a notched trowel is how it is applied. The placed mixture should be rolled with a spike roller to remove any trapped air bubbles. When the temperature falls below 10°C, the relative humidity rises beyond 90%, or there is rain, fog, or mist, do not apply. To limit the possibility of condensation, the substrate must be 3°C above the dew point.

Disclaimer: These parameters describe our product's overall quality and may differ from batch to batch and producer to producer. If you want specific specs, please contact us by phone or email.

Packaging:

Part A-20 kg, Part B-10 Kg, 30Kg Sand filler.

Shelf Life:

Part A, Part B 12 months from the date of manufacturing.

Storage Condition:

The product must be kept dry, between 5 and 35 degrees Celsius, in its original, unopened, and undamaged sealed package.

Points to Remember:

- Epoxy Primer FL should not be used on surfaces that are becoming more moist.
- Epoxy Primer FL that has just been applied needs to be protected from moisture, condensation, and dampness for at least 24 hours.
- For professional use only by experienced applicators.



EPOXY FLOORING TC (TOPCOAT)

Legal Notes: The information, and, in particular, the recommendations relating to the application and end-use of West Chem's products, are given in good faith based on West Chem's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with West Chem's recommendations. In practice, the difference in materials, substrates and actual site conditions are such that no warranty in respect of merchant ability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application & purpose. West Chem reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.